



# iShine

FLOOR SYSTEM



WWW.BARTELLGLOBAL.COM

## CANADA

SPE NA  
375 ANNAGEM BLVD,  
MISSISSAUGA, ON, L5T 3A7  
866-501-1683

## EUROPE

SPE INT  
HONEYHOLES LANE, DUNHOLME,  
LINCOLN, UK, LN2 3SU  
+44 (0)1673 860709

## USA EAST

INNOVATECH  
832 80TH STREET SW  
EVERETT, WASHINGTON, 98203  
800-267-6682

## USA WEST

BARTELL MORRISON USA  
200 COMMERCE DRIVE, UNIT A  
FREEHOLD, NEW JERSEY, 07728  
888-999-1570

# iShine

FLOOR SYSTEM

## ECONOMY

The iShine Floor System Economy Finish exists for the contractor who needs a good finish with a minimal amount of steps. When cost and time are big factors that cannot be wasted, the Economy Finish is the best solution for a professional grade surface on a budget. Like the rest of our system, this finish Shines.



WWW.BARTELLGLOBAL.COM

## ECONOMY

TRANSITIONAL		TRANSITIONAL
		100 RESIN
DENSIFIER		DENSIFY
POLISHING		200 RESIN
		400 RESIN
SEALER		SEALER LG

### 1. TRANSITIONAL



Using the quick change TMAG resin adaptors, fasten the **transitional** tooling to the grinder. Grind in an “east to west” then “north to south” pattern, or until a uniform scratch pattern is achieved. Thoroughly inspect that scratches from previous step have been removed before moving on to the next step.

### 2. iSHINE 100



Squeegee or vacuum up dust residue from previous step, proceed to polish with **iSHINE100** Grit resin (BLACK). Polish in an “east to west” then “north to south” pattern, or until a uniform scratch pattern is achieved. Thoroughly inspect that scratches from previous step have been removed before moving on to the next step.

### 3. DENSIFY



Squeegee or vacuum up dust residue from previous step. Ensure that the surface is clean and dry before completing the densification process. For a Sodium based densifier apply **ArmorDefend Na**. For a Lithium based densifier apply **ArmorDefend Li**. Refer to the chosen products data sheet for safety and application instructions.

### 4. iSHINE 200 - iSHINE 400



After the densification process is complete, proceed with the remaining resin steps. Polish with **iSHINE 200** Grit resin (BLUE). Polish in an “east to west” then “north to south” pattern, or until a uniform scratch pattern is achieved. Thoroughly inspect that scratches from previous step have been removed before moving on to the next step. Squeegee or vacuum up dust residue from the previous step if required. Repeat this process for **iSHINE 400** grit (RED).

### 5. LOW GLOSS SEALER



Squeegee or vacuum up dust residue from previous step. Ensure that the surface is clean and dry before completing the **ArmorFinish**: Stain and wear protection. Refer to the product data sheet for safety and application instructions.

## TMAG

Our TMAG Series was developed with you in mind. When you're out on a site, getting ready to open up the floor, the last thing you want to do is fiddle around with bolts. With our quick-change magnetic plates, we make it easy. For those jobs where magnets are not enough, we have a standard 3 hole pattern to give the extra hold.

## iSHINE

Our iShine series is made up of three different resin options. We have 3” pucks, flex pads, and RD discs. Our 3” pucks are great for general application. Flex pads are ideal for uneven slabs & restoration projects. Finally, RD discs are designed for flat floors and can withstand high temperatures. They have an extremely long life as well.

## ARMORDEFEND & ARMORFINISH

Our chemical line consists of a densifier (ArmorDefend) and a sealer (ArmorFinish). ArmorDefend comes in either Lithium or Sodium, depending on your preference or desired end product. We offer ArmorFinish in either a high gloss or a low gloss version to determine the end product. With these chemicals, your floor will be protected from stains & wear, keeping your floor pristine over time.

## BOND CHART

EXTRA HARD CONCRETE	HARD CONCRETE
X-SOFT BOND	SOFT BOND
MEDIUM CONCRETE	SOFT CONCRETE
MEDIUM BOND	HARD BOND